



Job File No.: 181202/65647-0001-1291/M-NK-2015

CERTIFICATE OF SAMPLING AND ANALYSIS

In pursuance of an order for inspection given to us

BY : " CARBO ONE LIMITED "
TO INSPECT : Coal 0-50 mm, grade "LV T-coal" (as declared) in rail cars
BY : Sampling and Analysis
AT : Kaltansky open cut, Kemerovo region, Russia
ON : 4 January 2015

WE HEREBY CERTIFY that we have performed sampling and analysis of the above mentioned commodity.

SAMPLING: Manual sampling as per ISO 18283 5.3. from the tops of the rail cars: Sampling material in motion, on systematic known mass intervals basis. Increments were collected from freshly exposed surface, on a mass interval basis, with fixed increment mass. Manual Sampling method was agreed with the SGS Principal, as sampling by other methods was not possible.

I. ANALYSES WERE PERFORMED IN SGS LABORATORY:

1. **Proximate analysis** was performed in SGS laboratory (Accreditation Certificate No. POCC U.0001.21TY38, valid till 22.09.2016) according to ISO Methods with results as follows:

Basis reported	Total moisture, % ISO 589-2003, ISO 5068-1- 2007	Ash, % ISO 1171-97	Yield of volatile matter, % ISO 562-98	Total sulphur, % ISO 19579-92	Gross calorific value, kcal/kg ISO 1928-76
As Received	5.4	16.9	10.5	0.39	6544
Air Dry Basis	0.7	17.8	11.0	0.41	6868
Dry Basis		17.9	11.1	0.41	6917
Dry Ash Free			13.5	0.51	8424

Net Calorific Value (as received) was calculated in accordance with ISO 1928:2009 (Pt. 12.2.2.1 и Pt E.3.3): 6366 kcal/kg

2. **Screen test** were performed in accordance with ISO 1953 with results as follows:

Nominal Top Size (mm)	+50	25-50	13-25	6-13	3-6	1-3	0.5- 1	0-0.5
Yield (%)	4.1	15.2	17.8	15.6	12.9	16.3	7.0	11.1

SGS Vostok Limited

312-24, Ordzhonikidze Street, 654005 Novokuznetsk

Russian Federation

t : +7 3843 39 16 81, 39 16 82, 39 16 83 f : +7 3843 39 12 42

e: ru.novokuznetsk@sgs.com

www.ru.sgs.com

Member of SGS Group

This document is issued by the Company subject to its General Conditions of Service (www.sgs.com/en/Terms-and-Conditions.aspx). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues established therein.

This document is to be treated as an original within the meaning of UCP 600. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



3. Determination of characteristics of hygroscopic moisture was performed in accordance with GOST 8719-90 with results as follows:

Hygroscopic moisture: 1.31

4. Determination of characteristics of plastic layer was performed in accordance with GOST 1186-87 with results as follows:

Attribute	Unit	Value
X	mm	14.0
Y	mm	0.0

5. Ultimate analysis was performed in accordance with ISO methods with results as follows:

Element	Percentage, %	Test's methods
	Dry Ash Free basis	
Carbon	90.14	ISO 625-96 (GOST 2408.1-95), ISO 609-96 (GOST 2408.4-98)
Hydrogen	4.14	
Nitrogen	2.24	ISO 333-83 (GOST 28743-95)
Oxygen	2.97	ISO 1994-76 (GOST 2408.3-95)

6. Determination of chemical composition of ash was performed in accordance with ASTM D 3682-87 (GOST 10538-87) methods with results as follows:

Compounds	Percentage, %
Silicon dioxide	57.22
Alumina	26.36
Iron trioxide	6.55
Titanium dioxide	0.93
Calcium oxide	3.32
Magnesium oxide	0.71
Potassium oxide	1.891
Sodium oxide	1.062
Sulphur trioxide	1.356
Phosphorus oxide	0.530
Manganese oxide	0.064

SGS Vostok Limited

312-24, Ordzhonikidze Street, 654005 Novokuznetsk

Russian Federation

t : +7 3843 39 16 81, 39 16 82, 39 16 83 f : +7 3843 39 12 42

e: ru.novokuznetsk@sgs.com

www.ru.sgs.com

Member of SGS Group

This document is issued by the Company subject to its General Conditions of Service (www.sgs.com/en/Terms-and-Conditions.aspx). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues established therein.

This document is to be treated as an original within the meaning of UCP 600. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



7. Determination of elements' content was performed in accordance with ISO and ASTM methods with results as follows:

Compounds	Percentage, %	Test's methods
Fluorine	0.011	ASTM D 3761-96
Chlorine	0.011	ISO 587-97 (GOST 9326-2002)
Arsenic	< 0.0005	ISO 601-81, ISO 2590-73 (GOST 10478-93)
Phosphorous	0.041	ISO 662-81 (GOST 1932-93)

8. Determination of free swelling Index was performed in accordance with ISO 501-81 (GOST 20330-91) with results as follows:

FSI 0.5

9. Determination of Grey-King coke type was performed in accordance with ISO 502-82 (GOST 16126-91) with results as follows:

GREY-KING COKE TYPE A

10. Determination of Roga Index was performed in accordance with ISO 335-74 (GOST 9318-91) with results as follows:

RI 0(2:4)

11. Determination of plasticity according to Gieseler was performed in accordance with ASTM D 2639-98 with results as follows:

Attribute	Unit	Value
Initial softening Temperature	°C	440
Max. Fluidity Temperature	°C	461
Resolidification Temperature	°C	482
Max. fluidity	ddpm	1

SGS Vostok Limited

312-24, Ordzhonikidze Street, 654005 Novokuznetsk

Russian Federation

t : +7 3843 39 16 81, 39 16 82, 39 16 83 f : +7 3843 39 12 42

e: ru.novokuznetsk@sgs.com

www.ru.sgs.com

Member of SGS Group

This document is issued by the Company subject to its General Conditions of Service (www.sgs.com/en/Terms-and-Conditions.aspx). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues established therein.

This document is to be treated as an original within the meaning of UCP 600. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



12. Audiber-Arnu Dilatometer test was performed in accordance with ISO 349-75 (GOST 13324-94) with results as follows:

Attribute	Unit	Value
Softening Temperature	°C	390.9
Max. Contraction Temperature	°C	482.5
Max. Dilatation Temperature	°C	-
Contraction	%	-5.2
Dilatation	%	-

13. Determination of Hardgrove Index was performed in accordance with ISO 5074-80 (GOST 15489.2-93) with results as follows:

HGI 68

14. Determination of actual density was performed in accordance with GOST 2160-92 with results as follows:

AD 1.39 g/cm³

15. Determination of ash fusibility was performed in accordance with ASTM D1857-87. The reported results are as follows:

Attribute	Unit	Value	
		Oxidizing	Reducing
Initial deformation temperature	°C	1441	1370
Softening temperature	°C	1481	1411
Hemispherical temperature	°C	1503	1435
Fluid temperature	°C	1538	1468

16. Determination of petrographic composition and metamorphism stage was performed in accordance with ISO 7404 with results as follows:

Composition		Percentage, %
Coal		93
Mineral inclusions	Clay	7
	Quartz	-
	Sulphide	-
	Carbonate	-

SGS Vostok Limited

312-24, Ordzhonikidze Street, 654005 Novokuznetsk

Russian Federation

t : +7 3843 39 16 81, 39 16 82, 39 16 83 f : +7 3843 39 12 42

e: ru.novokuznetsk@sgs.com

www.ru.sgs.com

Member of SGS Group

This document is issued by the Company subject to its General Conditions of Service (www.sgs.com/en/Terms-and-Conditions.aspx). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues established therein.

This document is to be treated as an original within the meaning of UCP 600. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



5. Microlythotype:

Microconstituent	Percentage, %
Vitrinite	39
Semivitrinite	15
Inertinite	46
Liptinite	-

Sum of the fusainized components

ΣOK 56 %

Rank V

Interval No.	Ro min	Ro max	Frequency, %
1	1.40	1.44	-
2	1.45	1.49	3
3	1.50	1.54	7
4	1.55	1.59	7
5	1.60	1.64	7
6	1.65	1.69	8
7	1.70	1.74	8
8	1.75	1.79	10
9	1.80	1.84	13
10	1.85	1.89	14
11	1.90	1.94	12
12	1.95	1.99	5
13	2.00	2.04	3
14	2.05	2.09	1
15	2.10	2.14	2
16	2.15	2.19	-

SGS Vostok Limited

312-24, Ordzhonikidze Street, 654005 Novokuznetsk

Russian Federation

t : +7 3843 39 16 81, 39 16 82, 39 16 83 f : +7 3843 39 12 42


e: ru.novokuznetsk@sgs.com

www.ru.sgs.com

Member of SGS Group

This document is issued by the Company subject to its General Conditions of Service (www.sgs.com/en/Terms-and-Conditions.aspx). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues established therein.

This document is to be treated as an original within the meaning of UCP 600. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

**Reflectance indices R_0 :**

Average	1.77
Minimum	1.40
Maximum	2.15
Standard deviation	0.155
Quantity of scissions	0

II. ANALYSES WERE PERFORMED IN SUBCONTRACTED LABORATORY:

The sample was sent to subcontracted laboratory OAO "Zapadno-Sibirski Ispytatelny Centr" (Accreditation Certificate No. POCC RU.0001.21 AЯ 07) for analysis, and the findings reported by OAO "Zapadno-Sibirski Ispytatelny Centr" were as follows:

1. Determination of elements' content was performed in accordance with GOST methods with results as follows:

Compounds	Percentage, %
Germanium	0.0002
Selenium	$<0.05 \cdot 10^{-4}$
Gallium	0.0008
Mercury	$0.05 \cdot 10^{-4}$

SGS Vostok Limited

312-24, Ordzhonikidze Street, 654005 Novokuznetsk

Russian Federation

t : +7 3843 39 16 81, 39 16 82, 39 16 83 f : +7 3843 39 12 42

e: ru.novokuznetsk@sgs.com

www.ru.sgs.com

Member of SGS Group

This document is issued by the Company subject to its General Conditions of Service (www.sgs.com/en/Terms-and-Conditions.aspx). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues established therein.

This document is to be treated as an original within the meaning of UCP 600. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



2. Determination of elements' content was performed in accordance with GOST methods with results as follows:

Element	Content, %	Element	Content, %	Element	Content, %
Ba	0.07	Cd	<0.001	Pb	<0.0002
Be	0.0002	Co	0.0002	Ag	<0.00001
B	0.007	Li	<0.001	Sc	0.0008
Bi	<0.0002	La	<0.001	Sr	0.1
V	0.001	Mn	0.02	Sb	<0.002
W	<0.002	Cu	0.0003	Ti	0.2
Yb	0.0004	Mo	0.0002	P	<0.1
Y	0.001	As	<0.01	Cr	<0.001
Nb	<0.001	Ni	0.0006	Ce	<0.02
Sn	<0.0002	Zr	0.02		
Zn	<0.003				

3. Determination of ash fusibility was performed in accordance with ISO 540-81(GOST 2057-94) with results as follows:

Attribute	Unit	Value / atmosphere
		Semireducing
Initial deformation temperature	°C	1460
Softening temperature	°C	1480
Hemispherical temperature	°C	1500
Fluid temperature	°C	>1500

This document is a witness of services in collection and processing of information rendering.

Signed and dated
in Novokuznetsk / ES
20 January 2015



For and on behalf of
SGS Vostok Limited

SGS Vostok Limited

312-24, Ordzhonikidze Street, 654005 Novokuznetsk

Russian Federation

t : +7 3843 39 16 81, 39 16 82, 39 16 83 f : +7 3843 39 12 42

e: ru.novokuznetsk@sgs.com

www.ru.sgs.com

Member of SGS Group

This document is issued by the Company subject to its General Conditions of Service (www.sgs.com/en/Terms-and-Conditions.aspx). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues established therein.

This document is to be treated as an original within the meaning of UCP 600. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.